



Tannery shop in the mid 19th century (Collection: C&D, American Company)

HEMLOCK LEATHER

The Federal Ordnance Department's "other" war

by David Jarnagin

Most of us know that the use of leather in the construction of weapons and equipment for warfare dates back thousands of years to the earliest days of man. However, you may not know that the process of tanning the raw hides of animals into leather using bark and other vegetable materials remained remarkably the same until only about one hundred fifty years ago. It was not until the late 19th century that significant industrial changes and a natural calamity forever changed the methods, quality and even appearance of leather. Today, much of the traditional tanning methods are largely forgotten even by commercial leather producers. More significantly for Civil War historians and collectors, our knowledge of war time leather manufacturing, the considerable problems leather tanning and dyeing wrought upon the Federal Ordnance Bureau and the tremendous effect on today's artifacts is also largely unknown. That is, until now.

In the mid-19th century the tanning processes were achieved by repeat soakings of the animal hide in the bark from trees mixed with other ingredients which generate an acidic chemical reaction that slowly turns the hides into leather. The "tannin" found in the bark is the central ingredient that preserves the hide - first by stopping natural decay then leaving the leather both flexible yet durable enough for extended use. The bark taken from Chestnut Oak and Hemlock trees were the two most commonly used by American tanners of the time. Chestnut Oak was mandated by the Federal War Department during the war because of its more acidic nature which aided the tanning process but more importantly, for its ability to hold the black leather dyes. It remained the most popular for only a short time after the war until significant industrial changes gradually replaced it and finally a natural blight in 1904 virtually wiped out the Chestnut Oak tree in America. The use of hemlock tree bark was also a big part of the

mid-19th century commercial leather tanning business.¹ However, one of the more obscure aspects of war time military leather production was the peculiar problems that the use of Hemlock tanning caused the Federal Ordnance Department (Photo 1).

To be sure, leather tanning was big business by 1860. The 1860 U.S. Census lists over sixty-three million dollars worth of leather sales most of this in the manufacture of shoes and boots by the 12,486 footwear firms then in the United States.² In 1858 alone, 610,000 ready-made boots and shoes were “exported” to Europe!³ For commercial tanners of the era the use of Hemlock tanned leather was clearly more profitable than Oak. In the 1860's it normally took from five to seven months to tan a hide. Since Hemlock had a higher percentage of tannin than Oak it thus shortened the tanning process by a month or more. Another advantage was that Hemlock tanned hides tended to be heavier and therefore brought more money because hides were sold by weight at that time rather than by square feet as they are today. However, the most interesting aspect of hemlock tanned leather and one that created enormous troubles for the Federal Ordnance Department during the war and for collector's today, was the inert tendency for the dyes of Hemlock tanned leather to fade, often quickly, from black to brown. A serious problem then and one today that often leads collector's to misidentify artifacts as Confederate, re-dye them or worse, even reject as illegitimate otherwise quality artifacts.

During the war, hundreds of thousands of troops signed up for service in the Federal armies and of course, they all needed leather accoutrements. Since the regulations called for black leather accoutrements and equipment the U.S. Army tried to keep hemlock tanned leather from being used due to the fading problem.⁴ However, this quickly became impossible to control. Huge amounts of leather were quickly needed and contract tanners were very skillful at subverting the ordnance department rules by substituting hemlock for oak. Quality control was further complicated by the fact that leather was dyed and finished at the tannery before equipment manufacturers received the hide, so the Ordnance inspectors could not easily tell what type of tanning agent had been used.

According to Ordnance records, hemlock leather could be “doctored” or bleached to match the color of oak tanned leather before being dyed. This could be done to such a degree that even expert inspectors had difficulty telling the difference.⁵ The following post war Ordnance Department report shows the extent of the problem.

“It is certain that large quantities of “doctored” hemlock-leather were sold for oak leather during the late war. In some cases where it was used for scabbards, or iron and steel came in contact with it the alum and salt and vitriol, &c., used to bleach it, rusted the iron and steel, and so betrayed its illegitimacy ; but thousands of sides were sold and used in blissful ignorance by all except the seller. If only deceit were practiced, it

¹ Professor H. Dussance, Chemist, *A New and Complete Treatise on the Arts of tanning, Currying, and Leather - Dressing*. (Philadelphia, Penn., Henry Carey Baird, T.K. and P.G Collins Printers, 1867), pg. 428. “A very large majority, perhaps eight-tenths, of all calf skins taken off in this country are tanned in hemlock bark”.

² Professor H. Dussance, Chemist, *A New and Complete Treatise on the Arts of tanning, Currying, and Leather - Dressing*. (Philadelphia, Penn., Henry Carey Baird, T.K. and P.G Collins Printers, 1867), pg. 20.

³ Thomas, P. Kettell, *Eighty Years' Progress of the United States*. (Hartford, Conn., L Stebbins), 1867, Pg. 316.

⁴ Paul Johnson, *Civil War Cartridge Boxes of the Union Infantryman*, (Lincoln, R.I., Andrew Mowbray Publisher, 1998), Pg. 176.

⁵ *Notes on Leather, Ordnance Notes, No. LXXII*, National Armory, Washington, October 10, 1877, pg. 576. Ordnance Memoranda forwarded to Chief of Ordnance Brig, Gen. S.V. Benet by J. G Benton. Lt. Col. cmdg. National Armory in Philadelphia, Pa. Authorized for publication by the Secretary of War. Photo copy of original in possession of the author.

would not be so utterly objectionable, but the quality of the leather is injured by this doctoring, and it further deteriorates by age.”⁶ The artifact photographs in Figures 2 and 3 illustrates that issue by showing cracks and deterioration in the grain surface caused by the interaction of bleaches or “doctoring” and, the common acids used in the tanning process. There is evidence that the Ordnance Department knew that hemlock leather was often bleached to help it pass as oak tanned. At least one leather contractor, Henry W. Oliver warned the Ordnance office in April of 1864 that, “*Eastern manufactures use inferior hemlock, bleached stock.*”⁷ (Photos 2A, 2B and 3).

There was another type of tanning process that should be mentioned- “Union-tanned” leather or “mixed” tannage. This method used a combination of both hemlock and oak bark as a tanning agent. The tanners of the time believed mixing hemlock and oak barks would produce leather of better quality than either bark by itself. Ratios of hemlock and oak barks would vary but leather produced in this manner apparently still had fading problems inherent with hemlock and were thus not acceptable to the Federal government.⁸ In December 1863, 546 cartridge boxes manufactured by contractor James Boyd were rejected as being made of mixed tanned leather. Boyd wrote to George D. Ramsay, Chief of Ordnance in an attempt to get the cartridge boxes accepted anyway by arguing the difficulties of maintaining a supply of oak tannage.

*“In making our proposal to furnish these accoutrements of mixed tanned leather, our object was not for the purpose of putting in stock that would cost less than oak, but because we can always obtain a sufficient supply of the mixed tannage in our market, & cannot obtain the oak, but we have put in the pure oak whenever we could obtain a lot that was suitable for any part of the work, as good oak leather cuts to better advantage than the mixed tannage.”*⁹ Nevertheless, shortages no doubt often forced the War Department to accept equipment of inferior leather. In fact, the Ordnance Bureau goes so far as to list all three types of leather in a July 1864 advertisement for contract bids stating, “*Separate bids will be received for the manufacture of these accoutrements of pure oak leather, of mixed tannage oak finish and all hemlock*”.¹⁰

After tanning the next step was for the leather to be dyed black to meet the regulation standard. At the time of the Civil War, the most common leather dyeing formula of the period combined a skillful blend of craftsmanship and a chemical reaction between the natural tannin found in bark and various other components most notably iron mordants. When the iron comes in contact with the tannin the leather turns black. This process, when done correctly on oak tanned leather, produces a deep, rich and permanent black color. But, it was far less successful on hemlock tanned leather.

If the tanners were so skillful in producing leather dye then why was hemlock tanned leather so incapable of holding dye? This question required an investigation into the

⁶ Quartermaster Report, January 20, 1877., John F. Ridgers, Captain and Military Storekeeper, Philadelphia Depot of the Quartermaster’s Department to Brig. Gen. M.C. Meigs, Quartermaster General, U.S.A. Washington DC, page 257. Photocopy of original in possession of the author.

⁷ James Boyd & Sons to Ramsey, Boston, Mass., April 30, 1864, National Archives Washington DC, Record Group 156, Entry 21, Box 233, Document #0-27.

Paul Johnson, *Civil War Cartridge Boxes of the Union Infantryman*, (Lincoln, R.I., Andrew Mowbray Publisher, 1998), pg. 235.

⁸ Campbell Morfit, *The Arts of Tanning, Currying and Leather Dressing, Theoretically and Practically Considered in All Their Details*, (Philadelphia, Pa. Henry Carey Baird, 1852), pg. 88.

⁹ James Boyd & Sons to Ramsey, Boston, Mass., December 24, 1863, National Archives Washington DC, Record Group 156, Entry 21, Box 215, Document # B-536.

¹⁰ Ramsey to Editor, Morning Chronicle, July 4, 1864, National Archives Washington DC, Record Group 156, Entry 13, Volume 3, Box 324.

chemical reaction processes of the period dyeing formulas. Experimentation by the author with several formulas including those found in some rare 19th century tanning books re-discovered what the early tanners knew all along - that hemlock tannin would not seriously bond with the iron mordants to change form and thus turn the leather black. However, it is clear tanners routinely dyed hemlock leather to black. But how ? Once again a formula from the old tanning books provided the answer in the form of a recipe for “stained” leather. This formula utilized logwood and Sal soda which when combined with hemlock leather tannin formed a chemical bond that would turn the leather black- if only temporarily. It also had the additional advantage of adding weight which was important because leather was sold by the pound until about 1885. Unfortunately, logwood eventually oxidizes, causing the iron to change form again and gradually return the leather from black back to brown¹¹ (Photo 4).

There is strong evidence of a second way that tanners blackened leather at the time of the Civil War. Most leather dyes were used on the *grain side or smooth* of the hide. However, this second type called “waxed” used common lamp black that was worked into the *flesh or rough* side of the leather. Waxing actually works quite well because the rough surface gives greater adherence to the lampblack.¹² Nevertheless, unscrupulous contract tanners would often wax hemlock tanned leather on the *smooth side* of the leather giving it the black appearance it needed to pass inspection. This apparently fooled the inspectors- at least temporarily. Unfortunately, as the finish wears off the lamp black returns to powder and falls off giving the leather a patchy, three-dimensional look. At first, this erroneous dye treatment was thought to be rare during the war however, after examination by the author of over one hundred artifacts a large quantity show this type of finish suggesting that it may have been a fairly common finish for hemlock tanned leather (Photo 5).

Interestingly, experiments by the author with the leather dyeing formula found in *The Ordnance Manual for the Use of the Officers of the United States Army* found it hopelessly inadequate for dyeing leather. However, experiments with other formulas found in the early tanning books were far more effective and predictable. But why ? Modern tanners suggest the reason was that early tanners were very evasive, competitive artisans that jealously guarded their trade secrets including dye formulas. They speculate that the Ordnance officers writing the manual relied upon these tanners to provide the dye formulas published in the manual. Modern analysis of this formula shows it to be, well, little more than simple black ink.

There was one other problem ordnance officers noted about the use of hemlock tanned leather. As noted in the Ordnance Report above, “doctored” hemlock tanned leather “*used for scabbards, or iron and steel came in contact with it, the alum and salt and vitriol, &c, used to bleach it rusted the iron and steel ...*”. Actually, it was not the bleaching that caused the rusting of metal but rather the overuse of acids added in the tanning process. Normal vegetable tanning such as with oak is accomplished in an acidic condition, with a pH in the 3.5 to 5.0 range. Hemlock bark has a problem in that it will not turn acidic on its own so the tanner routinely added sulfuric acid to facilitate the tanning process. However, the over use of this acid will certainly cause cracks in

¹¹ Professor H. Dussance, Chemist, *A New and Complete Treatise on the Arts of tanning, Currying, and Leather - Dressing*. (Philadelphia, Penn., Henry Carey Baird, T.K. and P.G Collins Printers, 1867), pg 428. “But if hemlock leather is used as at present, so imperfectly blacked that a few days wear will change the color to a *foxy brown*”.

¹² Campbell Morfit, *The Arts of Tanning, Currying and Leather Dressing, Theoretically and Practically Considered in All Their Details*, (Philadelphia, Pa. Henry Carey Baird, 1852), pgs. 493-495.

leather, as well as rust any iron or steel coming into contact with the leather if not neutralized, thus affecting the quality (See photos 1 & 2). The fact is, tanners did not use “alum and salt and vitriol” to bleach the leather as has been noted above but rather were simply tanning Hemlock using too much sulphuric acid. Acid that later affected the quality of the leather. This represents yet another instance in which the ordnance officers misunderstood the tanning process. The use of alum, salt and vitriol is not used to bleach leather but rather used an entirely different “mineral” tanning process of the period called “Hungary” tanning.¹³

Collectors should note that artifacts of the Civil War era found to be of the proper patterns and manufacture but brown in color are likely of hemlock tannage and still a very collectable item. More than likely they probably slipped through the inspection process or were purchased by states outside the Federal ordnance system. In fact, hemlock tanned leather artifacts may even have a greater value due to the fact that hemlock tanned items were generally rejected by the Ordnance Department. So, the next time you see a lovely brown cap pouch, cartridge box or belt, remember that it has a great history all its own. So please leave it brown (Photo 6).

Just how much leather was required to equip six hundred thousand Federal soldiers in the first year or so of the war ? To give you an idea, the U.S. Army’s 1862 Ordnance Manual lists the amount of leather required to make each of the military accoutrement items. According to the manual, the shell of eleven cartridge boxes could be cut from one side of heavy bridle leather. For the inner cover and pockets the manual specified that fifty of each item could be obtained from each side of light bridle leather. To make 600,000 cartridge boxes, approximately 54,546 sides of heavy bridle leather and 24,000 sides of light bridle leather would be needed. So, just for cartridge boxes a total of about 78,546 sides of leather were needed to equip the Federal Army. When one then considers what was required to make other items including cap boxes, belts, shoulder straps, bayonet scabbards, saddles, bridles, saddle bags, artillery harness and more, the demand for leather was staggering and must have nearly overwhelmed the Federal Ordnance system and the tanners ability to supply them!¹⁴

There can be no doubt the northern tanning industry provided an invaluable service to the war effort but not without questions of profiteering by some of their brethren. As can be seen, some contract tanners of the period were very adept and apparently quite successful at substituting hemlock tanned leather for oak and then, giving it the appearance of being properly dyed black. It also appears that ordnance officers were often being deliberately confused and misled by the tanning industry in order to accept improperly dyed hemlock tanned leather. This most certainly widened profit margins at the expense of the regulations and sometimes the quality of equipment being issued and yet, it may have been condoned to some extent. Although it is not clear how successful ordnance inspectors were at detecting poorly dyed equipments the large number of surviving hemlock tanned equipments and contemporary documentation clearly indicate a significant number were made and issued into the field. One can only speculate but, given the heavy strain on tanneries and the colossal need for leather it is probable neither the Ordnance Department nor their finishing contractors had the luxury to be too picky when it came to the leather they received.

¹³ Campbell Morfit, *The Arts of Tanning, Currying and Leather Dressing, Theoretically and Practically Considered in All Their Details*, (Philadelphia, Pa. Henry Carey Baird, 1852), pgs. 415-432.

¹⁴ *Ordnance Manual for the Use of the Officers of the United States Army*, Third Edition, (Philadelphia, J.B. Lippincott & Co., 1862), pg. 231

The following provides an insight into the resources required to operate a typical tannery in the 1840's. This information, graciously provided by Zadock Pratt comprises the acreage, bark, labor, work hours, freight, livestock, feed, hay and hides consumed to tan one million hides during a twenty year period (1825-1845) at his family's tannery in Prattville, N. Y.

3,666 acres of bark land - 10 square miles, 18 cords to the acre	
120,000 cords at \$ 3 per cord	\$ 360,000
No. of days' work peeling and piling bark	18,555
4 trees to the cord	475,200
120,000 loads, or cords - 264,000,000 lbs	132,000
1,444 acres of wood land - 32,000 loads, or cords, worth	\$ 32,000
35,380 bushels of oats, 2.6 per bushel	\$ 41,967
1,200 tons of hay at \$ 8 per ton	\$ 9,600
313,000 days work in tanner - 1,000 years labor at \$ 14 per month	\$ 168,000
Board at \$ 1.50 per week	\$ 87,000
500,000 hides, weighing 15,000,000 lbs	1,750,000
Cartage, 5,700 loads of 2,600 lbs. each (one pair horses)	
1,000,000 sides of sole leather at 18 lbs per side	18,000,000
Hides and leather, together	33,000,000
Cost of carting	\$ 52,800
3,000 lbs per load of leather one pair of horses	\$ 6,000
2,600 lbs per load of hides, one pair of horses	\$ 5,700
Freight of hides and leather between New York and Catskill	\$ 30,000
Equal to 118,000,000 leather at 7 cts. per pound	\$ 3,060,000
Lost and worn out about 100 horses, at \$ 75 each	\$ 7,500
Cost of wagons, at \$ 250 per year	\$ 5,000
Insurance on stock	\$ 12,000
Yearly expenses	\$ 300,000
Total expenses, about	\$ 6,000,000

About the author

David Jarnagin is part owner of C & D Jarnagin, the nation's largest manufacturers of 18th and 19th century military reenactment clothing and equipment. For twenty-two years, David's domain has been the company leather shop where they make authentic cartridge boxes, cap boxes, belts, bayonet scabbards, knapsacks, shoes and more. A passion for the study and experimentation with period leather tanning, dyeing, equipment manufacture and of course, the handling of thousands of artifacts have made David uniquely qualified in the subject of 19th century leather processes and leather equipment.

Author's note

The author would like to thank the following people for their gracious and immeasurable assistance in the research for this article : The Hon. Zadock Pratt of Pratt Tanneries, Prattville, N.Y. ; Paul D. Johnson ; Fred Gaede ; Shep Hermann ; Phil Varnick, Mike Cunningham and, for his writing and editorial contributions, Ken R. Knopp. I would be remiss if I did not thank all the Ordnance officers that kept the great records that made this article possible.